

AMENDMENTS TO THE CLAIMS:

The following is a complete listing of the claims and reflects all changes currently being made to the claims. This listing supersedes all earlier versions and all earlier listings of the claims:

1. (Currently Amended) A cosmetic composition comprising a first film forming siloxane polymer, and a second film forming polymer obtained by polymerizing siloxane monomers and at least one ~~monomer selected from the group consisting of~~ ethylenically unsaturated ~~monomers~~ monomer of the general formula:



wherein R_1 , and R_2 are each independently H, halogen, hydroxyl, fluoroalkyl, a C_{1-30} straight or branched chain alkyl, aryl, aralkyl; R_2 is a pyrrolidone, or a substituted or unsubstituted aromatic, alicyclic, or bicyclic ring where the substituents are C_{1-30} straight or branched chain alkyl, or COOM or OCOM herein M is a C_{1-30} straight or branched chain alkyl, pyrrolidone, or a substituted or unsubstituted aromatic, alicyclic, or bicyclic ring where the substituents are C_{1-30} straight or branched chain alkyl, and

wherein said polymers are solvated or dispersed in a cosmetically acceptable nonpolar oil.

2. (Original) The composition of claim 1 wherein the first film forming siloxane polymer is a silicone resin.
3. (Currently Amended) The composition of claim [[3]] 2 wherein the silicone resin is a T

resin, an MT resin, and MQ resin or mixtures thereof.

4. (Withdrawn) The composition of claim 3 wherein the silicone resin is a T resin.
5. (Withdrawn) The composition of claim 4 wherein the T resin comprises alkoxy and/or hydroxy groups.
6. (Withdrawn) The composition of claim 2 wherein the silicone resin is an MT resin.
7. (Withdrawn) The composition of claim 6 wherein the MT resin is of the general formula M_xT_y wherein M is $R_1R_2R_3SiO_{1/2}$; T is $RSiO_{3/2}$.
8. (Withdrawn) The composition of claim 7 wherein the MT resin additionally comprises one or more difunctional units.
9. (Original) The composition of claim 3 wherein the MQ resin is of the general formula M_xQ_y wherein M is $R_1R_2R_3SiO_{1/2}$; Q is $SiO_{4/2}$; R_1 , R_2 , and R_3 are each independently C_{1-30} straight or branched chain alkyl or phenyl; and x and y are each independently 1-1,000,000.
10. (Original) The composition of claim 9 wherein R_1 , R_2 , and R_3 are each independently methyl or phenyl.
11. (Original) The composition of claim 10 wherein the MQ resin has alkoxy or hydroxy functional groups.
12. (Previously Presented) The composition of claim 1 wherein the second film forming polymer is obtained by polymerizing one or more M, D, T, or Q units with one or more ethylenically unsaturated monomers.
13. Cancelled.
14. Cancelled.
15. (Currently Amended) The composition of claim [[14]] 1 wherein the ethylenically unsaturated monomer is an acrylate or methacrylate.

16. (Original) The composition of claim 15 wherein the second film forming polymer is a silicone acrylate copolymer.
17. (Original) The composition of claim 1 wherein the nonpolar oil is a paraffinic hydrocarbon.
18. (Original) The composition of claim 17 wherein the paraffinic hydrocarbon is volatile.
19. (Original) The composition of claim 1 which is an anhydrous pigmented composition.
20. (Original) The composition of claim 1 which is a lipstick.
21. (Previously Presented) The composition of claim 1 wherein the first film forming siloxane polymer is trimethylsiloxysilicate and the second film forming polymer is a copolymer of silicone and an ethylenically unsaturated monomer which is acrylic acid, methacrylic acid, or their simple esters.
22. (Previously Presented) The composition of claim 21 wherein the second film forming polymer is a copolymer of silicone and acrylic or methacrylic acid esters.
23. (Withdrawn) The composition of claim 1 wherein the first film forming siloxane polymer is polymethylsilsesquioxane.
24. (Withdrawn) The composition of claim 23 wherein the second film forming polymer is a copolymer of silicone and ethylenically unsaturated monomers which are acrylic acid, methacrylic acid, or their simple esters.
25. (Withdrawn) The composition of claim 24 wherein the second film forming polymer is a copolymer of silicone monomers and ethylenically unsaturated monomers that are esters of acrylic or methacrylic acid.
26. (Withdrawn) The composition of claim 23 wherein the second film forming polymer is a silicone acrylate copolymer.

27. (Previously Presented) The composition of claim 21 wherein the second film forming polymer is a silicone acrylate copolymer and the nonpolar oil comprises isododecane.
28. (Previously Presented) The composition of claim 21 wherein the second film forming polymer is a silicone acrylate copolymer and the nonpolar oil comprises cyclomethicone or linear volatile dimethicone.
29. (Previously Presented) The composition of claim 21 wherein the second film forming polymer is a silicone acrylate copolymer and the nonpolar oil comprises a nonvolatile silicone.
30. (Previously Presented) The composition of claim 29 wherein the nonvolatile silicone is dimethicone or a phenyl silicone.
31. (Previously Presented) The composition of claim 21 wherein the nonpolar oil is an ester having a viscosity ranging from about 2 to 1,000,000 centipoise at 25° C.
32. (Previously Presented) The composition of claim 21 further comprising a chemical or physical sunscreen.
33. (Previously Presented) The composition of claim 21 further comprising a gellant.
34. (Previously Presented) The composition of claim 33 wherein the gellant is a clay.
35. (Previously Presented) A color cosmetic composition comprising a first film forming polymer which is a silicone resin, and a second film forming polymer which is a silicone acrylate copolymer, and a nonpolar oil selected from a volatile paraffinic hydrogen, volatile silicone, or mixtures thereof, and pigments.